

## Ningbo Asia Pulp & Paper

### NINGBO FOLD

#### C1S Ivory

| Basis Weight            |                     | Thickness |          | Stiffness (Taber 15°) |      |
|-------------------------|---------------------|-----------|----------|-----------------------|------|
| g/m <sup>2</sup><br>±3% | 24"x36"<br>500 (lb) | µm (±4%)  | pt (±4%) | mN·m (±10%)           |      |
|                         |                     |           |          | CD                    | MD   |
| 190                     | 117                 | 245       | 9.6      | 1.7                   | 2.9  |
| 210                     | 129                 | 275       | 10.8     | 2.3                   | 3.9  |
| 220                     | 135                 | 290       | 11.4     | 2.6                   | 4.4  |
| 230                     | 141                 | 295       | 11.6     | 3.2                   | 7.2  |
| 250                     | 154                 | 340       | 13.4     | 4.1                   | 7.7  |
| 270                     | 166                 | 370       | 14.6     | 5.1                   | 8.3  |
| 300                     | 184                 | 415       | 16.3     | 7.1                   | 13.2 |
| 350                     | 215                 | 490       | 19.3     | 11.0                  | 22.0 |
| 400                     | 246                 | 555       | 21.9     | 15.4                  | 30.8 |

| Property             | Unit             | Value    |
|----------------------|------------------|----------|
| PPS (Top)            | µm               | ≤1.8     |
| Moisture             | %                | 6.0 ±1.5 |
| Brightness (Top)     | %                | 90 ±2    |
| 75°Gloss(Top)        | %                | ≥45      |
| IGT Blister(Top)     | m/s              | ≥1.0     |
| COBB Test(60s) (Top) | g/m <sup>2</sup> | ≤50      |
| PLY Bonding          | J/m <sup>2</sup> | ≥130     |

Test condition (ISO): temp 23±1°C, relative humidity 50±2%

Note: Shaded substances are non-regular substances which are not produced regularly.

Date: 12 Aug 2008