

CHENMING ART FBB SPECIFICATION

Grammage	g/m ²	210±3	230±3	250±3	300±5	350±5	400±5
Thickness	um	280±10	310±10	345±10	420±10	490±10	555±10
Stiffness	m N. m	5.5/3.0	8.0/4.0	9.2/4.5	16.0/9.0	29.0/13.5	38.5/16.5
Brightness	%	90.0-92.0					
Gloss	%	55-60					
Roughness	um	1.0-1.5					
Moisture	%	6.0-6.5					
Plybond	J/m ²	120-220					
Bulk	%	1.35-1.45					